

PRODUCT IDENTIFICATION

Product:	Thermofit 9mm (3/8")	Finishing treatment :	Fire retardant (on request)
Description:	THERMOFIT 9MM FELTVÄRI SERIE	Coating type :	None
Product type:	Needlepunch nonwoven	Cutting style :	Raw panel*
Fiber composition:	Polyester	*Must be cut to size.	

SPECIFICATIONS

Format : sheet

PROPERTY	TARGET	MIN	MAX	UNITS	METHOD	FREQUENCY
Thickness- Mean (man. - 10oz)	9	8	10	mm	ASTM-D5729/ MOD	N/A
Width	120	118	122	cm	ASTM-D461.9/ MOD	N/A
Length	244	242	246	cm	ASTM-D461.8/ MOD	N/A
Surface weight – Nominal (10"x10")	1350			g/m ²	ASTM-D3776/ MOD	N/A

FIRE RESISTANCE*


Tested in accordance with ASTM
E84 / UL 723

FSI : 5 (Class A)

SDI : 120 (Class A)

ACOUSTIC ASTM C423**

INDEX	A mounting
SAA	0.36
NRC	0.35



*Fire resistance is not part of a routine check. Results are based on testing performed initially on a representative sample of Thermofit 9mm 26-002-S0181 (UL 723).

**ASTM C423: Results are based on testing performed initially on a representative sample of the Thermofit.

QUALITY

Color variation may occur and is considered acceptable.

WARRANTY

The following warranty applies to Seller's Products only and excludes Seller's Services. If full payment for the Products is received, Seller warrants that at the time of shipment and for a period of one (1) year thereafter (unless a different period is specified by Seller) its Products (not including any parts, materials or equipment not manufactured or supplied by Seller) shall be substantially free of material defects in workmanship and material under normal use and service and shall substantially conform to contract specifications, subject to Seller's standard tolerances for variations. Buyer agrees to inspect the Products prior to acceptance and upon receipt and to give written notice within fifteen (15) days to Seller of any claim that the Products breach any warranty provided herein. Seller will be afforded a prompt opportunity to inspect the Products. If Buyer shall fail to give such notice or provide such opportunity to inspect, the Products shall be deemed accepted and to conform to the terms of the Agreement and Buyer shall be bound to accept and pay for the Products in accordance with the terms of the Agreement. Use or processing of the Products shall be deemed an unconditional acceptance. Defects in part of the Products shipped do not entitle rejection of the entire shipment.

For detailed information regarding Texel's (Alkegen) Terms and Conditions of Sale, please consult our website at: <https://texel.ca/en/terms-and-conditions/>.

END OF DOCUMENT